



# H350FG

## HOMOPOLYMER FOR FIBRE AND FILAMENT

Repol H350FG is recommended for use in compact **Fibre Spinning** operations, for making fine denier multifilament yarns and non-wovens. Repol H350FG has excellent uniformity needed for high speed spinning of fine deniers. Repol H350FG contains an excellent process stabilizer package suitable for non-woven and filament products. Formulated for gas fading resistance.

Typical Characteristics			
Property	Test Method	Unit	Typical Value*
Melt Flow Rate (230°C/2.16 kg)	ASTM D1238	g/10 min	35
Tensile Strength at Yield (50mm/min)	ASTM D638	MPa	34
Elongation at Yield (50mm/min)	ASTM D638	%	10
Flexural Modulus (1% secant)	ASTM D790A	MPa	1550
Notched Izod Impact Strength (23°C)	ASTM D256	J/m	22
Heat Deflection Temperature (455 kPa)	ASTM D648	°C	104

\* Typical values, not to be taken as specification. All the mechanical properties as per ASTM D638 Type I specimen injection moulded in accordance with ASTM D4101

### Applications

Fine fibre yarn, non-woven fabric

### Regulatory Information

Meets the requirements stipulated in IS 10910 on 'Specification for Polypropylene and its Copolymers for safe use in contact with foodstuff, pharmaceuticals, and drinking water'. Additives incorporated in this grade conform to the positive list of constituents as prescribed in IS 10909. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21, 177.1520, Olefin polymers

### Storage Recommendations

Bags should be stored in dry / closed conditions at temperatures below 50°C and protected from UV / direct sunlight

Reliance Industries Limited, Product - Application & Technology Group, PRTC,  
Swastik Mill Compound, V.N. Purav Marg, Chembur, Mumbai-400 071. Tel.: +91-22-6767 7000. E-mail: polymer\_patsupport@ril.com Website: www.ril.com

\* The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or otherwise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or international. \* The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorised agents, as the information and/or data is subject to change based on the research and development work undertaken by the company.

Updated as of Jan, 2013